

LEGACY ROOF ANTICORROSIVE SATIN

TDS22-9305

DESCRIPTION	A 100% acrylic roof paint for external use. Provides self-priming and flash rust inhibiting properties for optimum performance. It has a high level of pigmentation to give excellent coverage.
TYPICAL USES	General exterior finish for roofs comprised of metal tiles and corrugated iron.
PERFORMANCE	High quality 100% acrylic paint with excellent exterior durability. May be used direct to Galvanised Iron or Zinalume, for premium corrosion protection use over Trueprep Metal primers.
LIMITATIONS	Not for use on new concrete surfaces. Do not apply if the air or surface temperature during application and drying is likely to fall below 10oC. Disconnect roof downpipes until after the first shower of rain in order to flush away surplus non-toxic wetting agents before the surface is used for the collection of drinking water.
TECHNICAL DATA	Resin: Acrylic Product Type: Anticorrosive Roof Satin Solvent: Water Appearance: White Colour: All Colours Primer: Not applicable Durability: Excellent Thining and Clean Up: Water Pack Size: 10 VOC: 49-60 g/litre Vol Solids: 38 percent Touch Dry: 60 minutes @20°C Recoat Time: 2 Hours @20°C Number of Coats: 2 to 3 Theoretical Coverage: 10 m ² /litre/coat Wet Film Thickness: 100 microns Dry Film Thickness: 38 microns
AVAILABLE FINISHES @60°C	Sheen Satin 25%
SPREAD RATE	First Coat: 10 - m ² /litre/coat Second Coat: 12 - m ² /litre/coat Practical spreading rates will vary depending on such factors as application method, ambient conditions and surface porosity and roughness.
PRODUCT CODES	22-9305.10

SURFACE PREPARATION

Galvanised Steel and Zinalume-Previously Painted Good

If any areas of moss or mould infestation exist, treat them with TRUEPREP GREEN KILL, following instructions on TDS. Apply by flood coating to the surface and allow a minimum of 48 hours and up to four weeks for sterilization before scrubbing or water-blasting for removal of the detritus. For heavy infestations, longer dwell time or additional applications may be required.

Clean down using TRUEPREP SURFACE CLEAN applying by pump spray or broom. Additional scrubbing will assist in the breakdown and removal of any difficult contamination. Refer to TDS for application and dilution rates. Water blast or thoroughly rinse with high volume water to remove all dirt, grease and surface contamination.

Inspect the substrate prior to applying any coating system to ensure there are no surface defects exists. Repair as required.

Perform a crosscut adhesion test to several places across all elevations where existing coating are present to validate adhesion of the existing coating prior to overcoating. It is also recommended to apply TEST AREAS of the specified paint system to several places across all elevations to validate adhesion of the system AND mitigate risk of blistering that may occur between bare galvanised iron and the factory applied primer, or previous coatings. Contact Cotec Technical if you have any concerns, or reference MPNZA fact sheet #44.

Any areas of rust or corrosion or where original coating is through to the metal, must be abraded using wire brush, sandpaper, or Ultra-high pressure water blast to remove so little or no corrosion is left on the surface. Treat the entire surface TRUEPREP RUST KILL to remove residual rust, white rust and remaining surface contaminants and clean the metal prior to painting. Rinse clean as per manufacturers recommendations. If the substrate is not passivated in this way, it is likely that corrosion will occur under the new paint film.

All areas must be free of loose or flaking paint, where the coating is eroded or powdery the surface must be abraded using wire brushes, sandpaper or high-pressure water blast to ensure the best adhesion of the new paint. Feather all edges.

Any areas that are shiny (original gloss level) such as shaded areas must be sanded to knock the gloss and provide a key.

Do not expect paint to successfully bridge gaps and cracks.

Apply coat one immediately to prevent any contamination or further corrosion.

MIXING INSTRUCTIONS

Mix well before use. Box to ensure colour consistency, particularly on large areas.

APPLICATION

For corrugated iron add about 35% to the length x width of a roof to get actual "flat" surface area. For long run iron add about 45%.

SPRAY

515-19 thou tip. 2500 psi pressure

BRUSH/ROLLER

Roller (good quality 8-15 mm) or brush. Best spray applied (use airless spray (2500psi min), with tip 515 approx or larger). Apply 3 coats for maximum performance.

CLEAN UP

Water. Use a small amount of detergent to aid clean up.

APPLICATION NOTES

Allow to cure at least 6 hours at 15°C before subjecting to rain.

THINNING

Maximum thinning 5% Cotec Spray Thinner for spraying.

ENVIRONMENTAL

This formulation uses the latest technology with low toxicity, ensuring environmental issues are not compromised. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET

COATING TECHNOLOGIES LIMITED

10 Andromeda Crescent, East Tamaki, Auckland 2013 Ph +64 9 837 0897 www.cotec.co.nz

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.