

PROSPEC EX HIGH BUILD SATIN

TDS01-015

DESCRIPTION	An acrylic based exterior Wall paint. Specially formulated high build technology provides enhanced durability to exterior boardwall surfaces including timber and cementitious weatherboards, mortar renders, synthetic resin plasters, EIFS and solid masonry construction.
TYPICAL USES	Exterior walls.
PERFORMANCE	High build technology will provide a highly water repellent and a moisture vapour permeability coating with excellent durability.
LIMITATIONS	Do not apply if the air and surface temperature during application and drying is likely to fall below 10oC. Drying time will be impeded in areas where humidity is high. Available for sale only to approved applicators. Warranty is subject to Conditions outlined in the Prospec Exterior Product Warranty.
TECHNICAL DATA	Resin: Acrylic Solvent: Water Appearance: White Colour: All Colours Primer: See over. Durability: Excellent Thining and Clean Up: Water VOC: <40 g/litre Vol Solids: 46 percent Touch Dry: 30 minutes @15°C Recoat Time: 2 Hours @20°C Number of Coats: 2 Theoretical Coverage: 10 m ² /litre/coat Wet Film Thickness: 100 microns Dry Film Thickness: 46 microns
AVAILABLE FINISHES @60°C	Sheen 20%
SPREAD RATE	First Coat: 10 - m ² /litre/coat Practical spreading rates will vary depending on such factors as application method, ambient conditions and surface porosity and roughness.
PRODUCT CODES	01-015.04
SURFACE PREPARATION	Timber Dressed -New Unpainted STAINING All surface contaminants must be removed leaving the surface clean of dirt, grease and any other form of contamination. Ensure the timber is dry and has a moisture content of less than 15% before application. Inspect the substrate prior to applying any coating system to ensure there is no surface defects. DEFECTS: Repair or fill as required, taking care to use a filler of similar tone to the timber, prior to applying first coat. Sand all surfaces to be painted to an even flat smooth finish to provide a good key for the new paint system. Dust down and wipe with a damp cloth to remove all dust. Allow to dry.
APPLICATION	Pressure 2,500-2,900 psi, max. tip size 211 or 311. 60-100 mesh Gun filter Brush or roller (Wooster Pro-dooz 10-13mm nap dacron roller and premium brush). Add up to 5% Cotec Summer Retarder on hot, windy days to reduce drag and keep a wet edge.
THINNING	Water
ENVIRONMENTAL	This formulation uses the latest technology with low toxicity, ensuring environmental issues are not compromised. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET