

TRUEPREP RUST-KILL

TDS99-500

DESCRIPTION TRUEPREP RUST KILL – Rust Kill neutralises rust with Phosphoric Acid. It has no inbuilt primer.

TECHNICAL DATA

Vol Solids: 0 percent
Touch Dry: See parent product TDS
Recoat Time: See parent product TDS
Theoretical Coverage: 20 m²/litre/coat
Wet Film Thickness: 30 microns
Dry Film Thickness: 0 microns

SPREAD RATE

First Coat: 20 - m²/litre/coat
Practical spreading rates will vary depending on such factors as application method, ambient conditions and surface porosity and roughness.

PRODUCT CODES 99-500.05

SURFACE PREPARATION Decramastic-Aged Unpainted Good

Prior to working on the roof firstly access if the surface contains Asbestos. If it does ensure all work is carried out by a suitably qualified Asbestos Certified contractor to local council requirements.

If any areas of moss or mould infestation exist, treat them with TRUEPREP GREEN KILL, following instructions on TDS. Apply by flood coating to the surface and allow a minimum of 48 hours and up to four weeks for sterilization before scrubbing or water-blasting for removal of the detritus. For heavy infestations, longer dwell time or additional applications may be required.

Soft Wash using TRUEPREP SURFACE CLEAN applying by pump spray and broom. Additional scrubbing will assist in the breakdown and removal of any difficult contamination. Refer to TDS for application and dilution rates. Carefully water blast or thoroughly rinse with high volume water to remove all dirt, grease and surface contamination.

All areas of rust or corrosion must be abraded using wire brushes, grinder or sandpaper to remove so little or no corrosion is left on the surface. Ensure not to damage the integrity of the substrate.

Inspect the substrate prior to applying any coating system to ensure there are no surface defects exists.

SURFACE DEFECTS: Repair as required. Particular attention should be given to any dented/buckled tiles. Any tiles that cannot be repaired should be replaced. Check all fixings, ridges, flashings and valleys to repair if possible or replaced as required. At this stage identify areas requiring re-chipping and provision materials.

RUST: Treat the affected areas with TRUEPREP RUST KILL to remove residual rust, white rust and remaining surface contaminants and clean the metal prior to painting. Rinse clean as per manufacturers recommendations. If the substrate is not passivated in this way, it is likely that corrosion will occur under the new paint film.

When dry immediately apply specified coating system to prevent any contamination or further corrosion.

Decramastic-Previously Painted Good

Allow to Soft-Wash the Roof using TRUEPREP SURFACE CLEAN by pump spray or brush. Additional scrubbing will assist in the breakdown and removal of any difficult contamination. Refer to TDS for application and dilution rates. Wash down thoroughly to remove all dirt, grease and contaminates. Allow to fully dry prior to continuing.

If any areas of moss or mould infestation exist, treat them with our Trueprep Green Kill as per our TDS. Apply by flood coating to the surface and allow a minimum of 48 hours and preferably a week for sterilization before scrubbing or water-blasting for removal of the detritus.

For heavy infestations, an additional applications may be needed.

This process may take a few weeks to kill off the growth before it can be removed.

Rust: Ensure area to be treated is clean and free of wax, grease and contamination. Remove loose rust with a wire brush or grinder. Ensure not to damage the integrity of the substrate.

Apply Rust Kill with a paint brush, broom or Knapsack Sprayer and allow to penetrate for at least 30 minutes or until the rust changes colour. Thoroughly rinse with water to neutralise the Rust Kill and allow to fully dry prior to applying our specified metal primer and repair as usual.

Repairs

Inspection should be done to identify and if there are any dents in the chip-coated tiles. This should will be popped out where possible. Any tiles that can not be repaired should be replaced.

Check all ridges, flashings and valleys to repair if possible or replaced as required.

Decramastic-Aged Unpainted Poor

Prior to working on the roof firstly access if the surface contains Asbestos. If it does ensure all work is carried out by a suitably qualified Asbestos Certified contractor to local council requirements.

If any areas of moss or mould infestation exist, treat them with TRUEPREP GREEN KILL, following instructions on TDS. Apply by flood coating to the surface and allow a minimum of 48 hours and up to four weeks for sterilization before scrubbing or water-blasting for removal of the detritus. For heavy infestations, longer dwell time or additional applications may be required.

Soft Wash using TRUEPREP SURFACE CLEAN applying by pump spray and broom. Additional scrubbing will assist in the breakdown and removal of any difficult contamination. Refer to TDS for application and dilution rates. Carefully water blast or thoroughly rinse with high volume water to remove all dirt, grease and surface contamination.

All areas of rust or corrosion must be abraded using wire brushes, grinder or sandpaper to remove so little or no corrosion is left on the surface. Ensure not to damage the integrity of the substrate.

Inspect the substrate prior to applying any coating system to ensure there are no surface defects exists.

SURFACE DEFECTS: Repair as required. Particular attention should be given to any dented/buckled tiles. Any tiles that cannot be repaired should be replaced. Check all fixings, ridges, flashings and valleys to repair if possible or replaced as required. At this stage identify areas requiring re-chipping and provision materials.

RUST: Treat the affected areas with TRUEPREP RUST KILL to remove residual rust, white rust and remaining surface contaminants and clean the metal prior to painting. Rinse clean as per manufacturers recommendations. If the substrate is not passivated in this way, it is likely that corrosion will occur under the new paint film.

When dry immediately apply specified coating system to prevent any contamination or further corrosion.

COATING TECHNOLOGIES LIMITED

10 Andromeda Crescent, East Tamaki, Auckland 2013 Ph +64 9 837 0897 www.cotec.co.nz

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.

APPLICATION SAFETY PRECAUTIONS

- Appropriate PPE gear is required i.e., Goggles, Gloves, Masks etc.
 - Toxic if swallowed.
 - Causes severe skin burns and eye damage.
 - Ensure Knapsack Sprayer has brass fittings only.
 - Acutely toxic if swallowed. May cause burns to skin and eyes. Acutely toxic by skin absorption.
- Corrosive to skin. Corrosive to eye. Harmful to aquatic organisms. Harmful to terrestrial vertebrates.

- Ensure area to be treated is clean and free of wax, grease, loose paint and contamination.
- Remove loose rust with a wire brush or grinder.
- Apply Rust Kill with a paint brush, broom or Knapsack Sprayer and allow to penetrate for at least 30 minutes or until the rust changes colour.
- Rinse thoroughly with water to neutralise the Rust Kill and allow to dry.
-

Apply metal primer and repair as usual.

ENVIRONMENTAL This formulation uses the latest technology with low toxicity, ensuring environmental issues are not compromised. DO NOT POUR paint or wash down storm water or water courses. ALWAYS dispose of in accordance with local Government regulations. Soak up spills with absorbent material and dispose of properly. If spraying use suitable respiratory protection. Refer to the MATERIAL SAFETY DATA SHEET

COATING TECHNOLOGIES LIMITED

10 Andromeda Crescent, East Tamaki, Auckland 2013 Ph +64 9 837 0897 www.cotec.co.nz

Technical information given verbally or in writing is based on knowledge and research, given in good faith and believed to be reliable, but no guarantee of accuracy is made or implied. Since methods and conditions of use are beyond our control, all merchandise is sold and received subject to the condition that our liability whether express or implied for any defect in quality, or for any lack of fitness for the specified use thereof, is limited to the return of the purchase price if written claim is made within 14 days from the date of delivery. It is recommended that the user makes his or her own tests to determine the suitability of the product for his own requirements. Freedom from patent restrictions is not implied.